



PRODUCT DESCRIPTION

PlasDECK is a resilient flexible PVC synthetic teak decking that provides a superb skid-resistant surface.

Suitable Substrates

Fiberglass, wood, steel, aluminum

Applications

Installation of new synthetic teak, aftermarket marine teak decking or replacement for existing marine teak decks.

Thickness

Nominal Thickness: .165 (4.191 mm)

Weight

6 inch (152.4 mm) wide rolls weigh 19 lbs. (8.6kg)
2 inch (50.8 mm) wide rolls weigh 6.5 lbs. (2.95kg)

Colors

15 colors available

Composition

Plasdeck is composed of non-migrating plastisizers, polyvinyl chloride compounds, UV protective agents, antimicrobial additives & pigments.

Storage

Keep materials lying upright standing on roll edges. Keep decking rolled the same direction as it was received and keep clean and dust free.

Site Conditions

Storage of materials and work area need to be around the same temperature. If not, allow material to sit in work area for 30 minutes. Install decking in temperatures between 60°-95° F (16°-35° C)

Set times

All adhesives are moisture cure and open time will depend on the climate. Higher the humidity, less work time you will have.

Sausage Glue: Open Time > 30 minutes
Skin Forming = 20 minutes

Caulk Glue: Open Time > 15 minutes
Skin Time = 10 minutes

Technical Info

We understand our products are different from traditional teak decking & you will probably have questions. Our products are designed for your custom install, so we are ready for any and all questions you may have. Please call or email your questions. 1.800.320.1841 info@plasdeck.com

INSTALLATION

Allow time for material to relax. Dry fit and cut pieces to size. Trowel out PlasDECK adhesive, lay material into glue and then slide into next piece. Roll immediately. Caution; knees can leave depressions into glue so be careful on how you work through your layout. For more thorough instructions please view our installation guide on our website; www.plasdeck.com

Subfloor Considerations

Substrate must be clean, dry, smooth and stable. Must wipe down surface and back of material with denatured alcohol for superior adhesion.

Post Installation

Allow adhesive to set with no traffic for 18-24 hours. If other work is going on, clean and vacuum up any debris and cover area with kraftpaper to guard against any damage. Wipe any excess adhesive up with denatured alcohol.

Warranty

PlasDECK warrants to the purchaser of its products for a period of five (5) years from the date of purchase. During these warranted periods of time the products will be free from defects in material and workmanship and will not split, crack, peel, rot, or be subject to wood boring insect damage. Material found to have split or cracked due to improper installation will not be warranted.

PlasDECK's sole obligation shall be to replace the quantity of its products proven to be defective and shall not be liable for any loss or damage.

PlasDECK does not guarantee the appropriateness of this material for any application without prior testing.

Any claims under this Limited Warranty must be made within five (5) years of purchase of the PlasDECK product, must be in writing accompanied by proof of purchase and must include the return of the defective product, freight prepaid, to PlasDECK. Replacement will be shipped freight collect.

THE ABOVE EXPRESS LIMITED WARRANTIES ARE THE SOLE AND EXCLUSIVE WARRANTIES AVAILABLE TO YOU. NO OTHER EXPRESS WARRANTIES ARE MADE. ALL IMPLIED WARRANTIES INCLUDING BUT NOT LIMITED TO WARRANTY OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE OR USE ARE EXCLUDED. IN NO EVENT SHALL PLASDECK BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.