

# PlasDECK

## PRODUCT DATA

### TYPICAL PHYSICAL PROPERTIES OF PLASDECK MATERIAL COMPOUND

	PROPERTIES	ASTM
Hardness, (Shore 'A' Duro +/-3) Delay, 15 Second Reading (Hand)	88	D-2240
Specific Gravity (+/-0.02)	1.40	D-792
Tensile Strength @ Break, (psi)	3078	D-638
Elongation, @ Break, %	380	D-638
Brittle Point °C	-18	D-746

(1097537)

6/17 - lmo

**TYPICAL PROPERTIES: THESE ARE NOT TO BE CONSTRUED AS SPECIFICATIONS**

#### **PlasDECK, Inc.**

3489 Sawmill Road, P.O. Box 4290, Akron OH 44321-0290  
fax 1-330-666-0844 - 1-330-668-2587 - 1-800-320-1841  
[www.PlasDECK.com](http://www.PlasDECK.com)